PRODUCT DATA SHEET

Avery Dennison® 2920 QM Ultra Destructible

Introduction

Avery Dennison 2920 QM is a special, ultra destructible film, especially designed and formulated to obtain tamper proof graphics and labels for safety and security applications.

Description

Facefilm: 60 micron, brittle, matt white, cast vinyl film

Adhesive: permanent, acrylic based

Backing paper: one side coated white kraft paper, 140 g/m²

Conversion

Screenprinting is recommended. Avery Dennison 2920 QM can also be die-cut with high quality steel rule dies.

For screen ink recommendations, please consult Avery Dennison Technical Bulletin 2.2.

Features

- Excellent destructibility and high vandal resistance.
- Outstanding durability and excellent outdoor performance.
- High opacity for superior hiding power.
- Excellent dimensional stability and printability.
- Smooth matt surface for superior appearance.

Recommendations for use

- Identification markings, instruction panels for manufacturing equipment.
- Nameplates, schematics on mechanical and electrical appliances.
- Permanent warning signs and emblems.
- Vehicle registration and safety inspection labels.
- Non-removable guarantee labels.

issued: 05/2015

PRODUCT CHARACTERISTICS

Avery Dennison® 2920 QM Ultra Destructible

Physical properties

 Features
 Test method¹
 Results

 Caliper, facefilm
 ISO 534
 60 micron

 Tensile strength
 DIN 53455
 1,0 kN/m

 Elongation
 DIN 53455
 10 %

 Dimensional stability
 FINAT FTM 14
 0,2 mm max.

Adhesion, initial FINAT FTM-1, stainless steel 600 N/m
Adhesion, ultimate FINAT FTM-1, stainless steel 800 N/m
Flammability Self extinguishing

Sholf life Stored at 22° C/50-55 % PH 2 years

Shelf life Stored at 22° C/50-55 % RH 2 years Durability² Vertical exposure 5 years

Temperature range

Features Results
Minimum application temperature +10° C

Service temperature: - 50° to +110° C

Chemical properties

FeaturesTest method¹ResultsHumidity resistance120 hours exposureNo effect

Corrosion resistance 120 hours exposure No contribution to corrosion

Water resistance 48 hours immersion No effect
Chemical resistance 48 hours immersion No effect
No effect
No effect

Solvent resistance Applied to aluminium, exposed to: No effect oils, greases, aliphatic solvents,

motor oils, heptane, kersosene and JP-4 fuel.

Important

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change.

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com

1) Test methods

More information about our test methods can be found on our website.

2) Durability

The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.

