PRODUCTDATA

Digital

Last change: March 28, 2018



be.tex® Samba FR | Product no.: 4384-6266

Woven





















PRODUCT FFATURES			

Material: 100% polyester

Weight: 195 g/m² Thickness: 250 µm Stretch: < 1 %

Transmission factor: 38 % Whitepoint: 94, 1, -6 L*a*b WIDTH (cm)

ca. 160 ca. 260 ca. 320 LENGTH (m)

ca. 70 ca. 100

ca. 100

APPLICATIONS

inflatables display frame systems light boxes

pop up display systems bean bags

table cloth banners

tents / parasols

FEATURES

air tight water tight no fraying good flatness crease free lotus effect

light diffusion coating

DESCRIPTION

Topseller and market standard for light boxes. Perfect backlighting characteristics and color-intensive print features. Absolutely crease free, therefore perfect for folded shipment, sun umbrellas, tents, blow-ups, beanbags, lightboxes, aluframes, etc. be.tex® Samba FR is even unlit and unprinted an absolute allrounder. Uncoated side with Lotus-effect. Water column coated side > 900 mm, uncoated side > 650 mm.

NOTES

The numbers above are purely guidelines and may differ depending on your personal printing needs and expectations. Since the printing results depend on numerous factors, we strongly advise to test your output in order to find out if any adjustments are necessary. A legally binding assurance of certain properties of the fabric can not be derived from the information above.

PRODUCTDATA

Digital

Last change: March 28, 2018



Dye sub paper transfer on uncoated side: self-tests are recommended. For Latex prints with a very high ink-load (backlit) self-tests are recommended. Do not use self-adhesive products as flat profile 4545-1sk for processing (lotus on the back). Technical textiles are naturally subject to weather conditions. This product can be used outdoor for a short term. When handled carefully this fabric can be even folded after printing.

The numbers above are purely guidelines and may differ depending on your personal printing needs and expectations. Since the printing results depend on numerous factors, we strongly advise to test your output in order to find out if any adjustments are necessary. A legally binding assurance of certain properties of the fabric can not be derived from the information above.